PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 :
B23K 35/34, C04B 37/00, 37/02, 41/87, C23C 24/08, C04B 41/88

A1

(11) International Publication Number: WO 94/16859

(43) International Publication Date: 4 August 1994 (04.08.94)

(21) International Application Number: PCT/US93/00661

(22) International Filing Date: 25 January 1993 (25.01.93)

(71) Applicant: UNIVERSITY OF CINCINNATI [US/US]; Mail Location 627, Cincinnati, OH 45221-0627 (US).

(72) Inventors: SEKHAR, Jainagesh, A.; 2310 East Hill, Cincinnati, OH 45208 (US). SUBRAMANIAN, Vidya; 618 Riddle Road, Apartment 1, Cincinnati, OH 45220 (US). NECIP, Suat, Canarslan; 508 Riddle Road, Apartment 45, Cincinnati, OH 45220 (US).

(74) Agents: DESHMUKH, Jay, R. et al.; Frost & Jacobs, 2500 Central Trust Center, 201 East Fifth Street, Cincinnati, OH 45202 (US).

(81) Designated States: CA, HU, JP, KR, PL, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published
With international search report.

(54) Title: COMBUSTIBLE SLURRY FOR JOINING METALLIC OR CERAMIC SURFACES OR FOR COATING METALLIC, CERAMIC AND REFRACTORY SURFACES

(57) Abstract

A slurry for joining metallic or ceramic surfaces or for coating metallic or ceramic and refractory surfaces, comprising a liquid suspending medium and at least two constituents in particulate form suspended in the medium, the constituents being so selected and proportioned as to undergo combustion synthesis when ignited. A method for coating or joining metallic or ceramic surfaces comprises applying such a slurry to a surface to be coated or to surfaces to be joined, and igniting the slurry to cause combustion synthesis.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria
AU	Australia
BB	Barbados
BE	Belgium
BF	Burkina Faso
BG	Bulgaria
BJ	Benin
BR	Brazil
BY	Belarus
CA	Canada
CF	Central African Republic
CG	Congo
CH	Switzerland
CI	Côte d'Ivoire
CM	Cameroon
CN	China
CS	Czechoslovakia
CZ	Czech Republic
DE	Germany
DK	Denmark
ES	Spain
FI	Finland
FR	France
GA	Gabon
GB	United Kingdom
GE	Georgia
GN	Guinea
GR	Greece
HU	Hungary
IE	Ireland
IT	Italy
JP	Japan
KE	Kenya
KG	Kyrgystan
KP	Democratic People's Republic of Korea
KR	Republic of Korea
KZ	Kazakhstan
LI	Liechtenstein
LK	Sri Lanka
LU	Luxembourg
LV	Latvia
MC	Monaco
MD	Republic of Moldova
MG	Madagascar
ML	Mali
MN	Mongolia
MR	Mauritania
MW	Malawi
NE	Niger
NL	Netherlands
NO	Norway
NZ	New Zealand
PL	Poland
PT	Portugal
RO	Romania
RU	Russian Federation
SD	Sudan
SE	Sweden
SI	Slovenia
SK	Slovakia
SN	Senegal
TD	Chad
TG	Togo
TJ	Tajikistan
TT	Trinidad and Tobago
UA	Ukraine
US	United States of America
UZ	Uzbekistan
VN	Viet Nam

COMBUSTIBLE SLURRY FOR JOINING METALLIC OR CERAMIC SURFACES OR FOR COATING METALLIC, CERAMIC AND REFRACTORY SURFACES

THIS IS A CONTINUATION-IN-PART OF APPLICATION SERIAL NO. 07/753,216 FILED AUGUST 30, 1991

BACKGROUND OF THE INVENTION

1. Field of The Invention

The present invention relates to a slurry which undergoes exothermic reaction by combustion synthesis when ignited, and methods for the use thereof in joining metallic or ceramic surfaces or for coating metallic, ceramic and refractory surfaces. Although not so limited, slurries of the invention have particular utility in joining stainless steel, aluminum, carbon steel and copper workpieces and in forming coatings on porous silica or aluminum oxide substrates which resist chemical attack, ingress and attack by molten alloys having high melting temperatures.

2. Prior Art

Joints between metal pieces are conventionally formed by welding or brazing, by means of a wide variety of techniques using an oxyacetylene torch, or the like. Brazing compositions for joining metal pieces by fusion are also well known. To the best of applicant's knowledge there have been no suggestions in the prior art to use a slurry for joining metallic pieces, the constituents of which are so selected and proportioned as to undergo exothermic reaction by combustion synthesis when ignited, thereby welding the metal pieces together.

Ceramic materials such as silica, alumina,

zirconia and the like are used for containing molten metals, in furnaces for melting metals, in armor for missiles and the like, as infrared sensors, in electronic packaging, in engine materials, and in related applications. Such ceramic materials are frequently porous because they are made from powders which are sintered. Although porosity may be beneficial in imparting low density and specific toughness, porosity is detrimental from the standpoint of chemical attack, ingress into the ceramic or refractory material and resistance against attack by molten alloys at high temperature. Expensive fabrication is necessary to obtain a ceramic material of the above type in a fully densified condition. The prior art has resorted to coating ceramic surfaces in order to eliminate ingress or diffusion of material such as molten metal into the ceramic. No generally suitable technique is known to applicant to solve the problems inherent in coating ceramic or refractory surfaces.

Despite the existence of a wide variety of welding and brazing techniques and compositions, and despite the prior art suggestions for coating porous ceramic or refractory surfaces, a genuine need exists for alternative compositions and methods for joining metallic or ceramic surfaces or for coating metallic, ceramic and refractory surfaces.

SUMMARY OF THE INVENTION

It is an object of the invention to provide a slurry for joining metallic or ceramic surfaces or

for coating metallic, ceramic and refractory surfaces, by the use of constituents which undergo exothermic reaction by combustion synthesis.

It is a further object of the invention to provide methods for joining metal or ceramic surfaces and for coating metallic, ceramic and refractory surfaces by means of slurries which undergo exothermic reaction by combustion synthesis.

According to the invention there is provided a slurry for joining metallic or ceramic surfaces or for coating metallic or ceramic and refractory surfaces, the slurry comprising a liquid suspending medium and at least two constituents suspended in particulate form in the medium and selected from the group consisting of titanium dioxide, boron oxide, aluminum oxide, aluminum, silicon, titanium, boron, nickel, phosphorus, chromic oxide, carbon, niobium, zirconium, tantalum, molybdenum, hafnium, and vanadium, the constituents being so selected and proportioned as to undergo exothermic reaction by combustion synthesis when ignited.

Liquid suspending mediums are monoaluminum phosphate, colloidal silica, methyl cellulose, alcohols, acetone, water, sodium silicate, and combinations of common acids and bases.

Optionally, the slurry may also contain diluents or reinforcing agents, which do not undergo combustion synthesis, in particulate form, including but not limited to metals such as aluminum, iron, copper and silver, and non-metallics such as borides, carbides, nitrides,

oxides and silicides of titanium, niobium, and chromium.

A slurry for coating metallic or ceramic and refractory surfaces, in accordance with the invention, comprises a liquid suspending medium and particulate constituents suspended in the medium capable of undergoing exothermic reaction by combustion synthesis when ignited, the constituents being selected from the group consisting of titanium and crystalline carbon; titanium and amorphous carbon; titanium and aluminum; aluminum, titanium dioxide, and boron oxide; aluminum oxide, titanium, and amorphous carbon; and mixtures thereof.

A slurry for joining metallic or ceramic surfaces, in accordance with the invention, comprises a liquid suspending medium and particulate constituents suspended in the medium capable of undergoing exothermic reaction by combustion synthesis when ignited, the constituents being selected from the group consisting of titanium dioxide, boron oxide, aluminum, titanium, boron, nickel and phosphorus; titanium and boron; titanium, boron, nickel and phosphorus; chromic oxide, carbon and aluminum; and mixtures thereof.

A method of coating metallic or ceramic and refractory surfaces in accordance with the invention comprises the steps of providing a slurry having a liquid suspending medium and particulate constituents suspended in the medium capable of undergoing exothermic reaction by combustion synthesis when ignited, the constituents being

selected from the group consisting of titanium and crystalline carbon; titanium and amorphous carbon; titanium and aluminum; aluminum, titanium dioxide and boron oxide; aluminum oxide, titanium, and amorphous carbon; and mixtures thereof; applying the slurry to a metallic, ceramic or refractory surface so as to form a layer of uniform thickness thereon; and igniting the layer to cause combustion synthesis thereof; thereby forming an adherent coating of titanium carbide; titanium aluminide; a titanium boride and aluminum oxide composite; or an aluminum oxide, titanium dioxide and titanium carbide composite .

The invention further provides a method of joining metallic or ceramic surfaces, which comprises the steps of providing a slurry having a liquid suspending medium and particulate constituents suspended in the medium capable of undergoing exothermic reaction by combustion synthesis when ignited, the constituents being selected from the group consisting of titanium dioxide, boron oxide, aluminum, titanium, boron, nickel and phosphorus; titanium and boron; titanium, boron, nickel and phosphorus; chromic oxide, carbon and aluminum; and mixtures thereof; applying the slurry to metallic or ceramic surfaces to be joined, placing the metallic or ceramic surfaces in abutting relation with the applied slurry therebetween; and igniting the slurry to cause combustion synthesis thereof at a temperature sufficient to fuse the metallic or ceramic surfaces together.

DETAILED DESCRIPTION OF THE INVENTION

In the embodiment of the invention adapted for coating ceramic and refractory surfaces, preferred particulate constituents comprise, in weight percent based on the total weight of constituents, the following groups:

from 75% to 85% titanium, and 15% to 25% crystalline carbon;

from 75% to 85% titanium, and 15% to 25% amorphous carbon;

from 60% to 68% titanium, and 32% to 40% aluminum;

from 35% to 41% aluminum, 30% to 36% titanium dioxide, and 27% to 31% boron oxide;

from 50% to 97.5% aluminum oxide, 2% to 25% titanium, and 0.5% to 25% amorphous carbon.

A preferred liquid suspending medium for the slurry is monoaluminum phosphate and/or colloidal silica. Both these liquids are reactive with the reactants, which is desirable since they become an integral part of the final coating.

Water and acetone were also tested as liquid suspending mediums and found to be unsatisfactory since the low evaporation temperatures thereof resulted in cracks and distortion in the coatings during drying.

In the embodiment of a slurry adapted for joining metallic surfaces, preferred particulate constituents comprise, in weight percent based on the total weight of the constituents, the following groups:

from 28% to 32% titanium dioxide, 25% to 27% boron oxide, 32% to 35% aluminum, 3% to 4% titanium, 1.5% to 2.0% boron, 3.8% to 4.5% nickel, and 0.7% to 1.1% phosphorous;

from 60% to 70% titanium, and 30% to 40% boron;

from 30% to 35% titanium, 15% to 20% boron, 38% to 44% nickel, and 8% to 10% phosphorus;

from 12% to 20% titanium dioxide, 10% to 16% boron oxide, 15% to 20% aluminum, 0 to 10% iron, 15% to 17.5% titanium, 8% to 9.5% boron, 19% to 22% nickel, and 4% to 5% phosphorus;

from 67% to 70% chromic oxide, 6.5% to 8% carbon, and 23% to 26% aluminum.

All constituents should have an average particle size of less than 53 microns (i.e., passing 270 mesh screen). Materials are generally available having average particle sizes of -300 or -325 mesh screen.

The amount of liquid suspending medium is not critical and is selected to provide a viscosity suitable to permit application by painting, spraying or dipping, while at the same time

avoiding excessive run-off. When coating metallic or ceramic or refractory surfaces, it is preferred to form a layer of slurry having a thickness of about 0.2 to 0.3 mm. In general, from about 1 to about 12 parts by weight of the powdered constituents are dispersed uniformly in from about 2 to about 5 parts by volume of the liquid suspending medium, although these limits can be varied depending upon the particular mixture of constituents.

Tests have been conducted on slurries for coating ceramic surfaces. For test purposes five examples of powdered constituents were prepared as follows:

Example 1 - titanium 80%, crystalline carbon 20%

Example 2 - titanium 80%, amorphous carbon 20%

Example 3 - titanium 64%, aluminum 36%

Example 4 - titanium dioxide 33%, boron oxide 29%, aluminum 38%.

Example 5 - aluminum oxide 95-97.5%, titanium 2-4%, amorphous carbon 0.5-1%.

The percentages above are by weight. The titanium, carbon, and aluminum powders were obtained from ALFA or from Johnson Matthey Electric and ranged in purity from 99.0% to 99.5%. The crystalline and amorphous carbon powders were -300 mesh particle size, while the titanium and aluminum powders were -325 mesh. Titanium dioxide and boron

oxide were obtained from Fisher, grade designations LO-904811 and LO-904641, respectively. Aluminum oxide was obtained from Alcoa Chemicals, grade designation A-17. Slurries were prepared by mixing uniformly 1 part by weight of the powders of the above examples with 2 parts by volume of each of four different liquid suspension media, viz., water, colloidal silica, monoalunimum phosphate and acetone, for Examples 1-4. As indicated above, preliminary tests indicated that water and acetone were unsuitable, and hence were not subjected to further tests. Monoaluminum phosphate (MAP) was found to be the preferred suspension medium.

For Example 5, the liquid suspension media were MAP 90% and colloidal silica 10% by volume, and MAP 95% and colloidal silica 5% by volume. The colloidal silica was REMET-SP30. Slurries were prepared by mixing uniformly 1 part by weight of the powder with 1.5 part by volume of suspension medium.

Fused silica substrates were coated by painting to form a layer of 0.25 mm (250 microns) thickness with slurries of each of the above examples 1-4 in MAP. After coating, reaction was initiated either by a wave propagation mode or thermal explosion mode of reaction in air.

In the wave propagation mode, reaction was started from one part of the sample with a butane flame torch, and the reaction then self-propagated across the sample. Since each of examples 1-4 had a different heat of reaction, it was necessary to heat samples to different initial temperatures to

sustain the combustion synthesis.

In the thermal explosion mode reaction was started simultaneously in all parts of the sample subsequent to a heating and drying step. Samples of Examples 1-4 were heated from room temperature to 1000° C and then cooled slowly in a furnace to avoid possible surface cracks in the coatings. The thermal explosion mode in air is the preferred method.

Examples 1-4 reacted by combustion synthesis as follows:

1. Ti+C (crystalline → TiC
2. Ti+C (amorphous) → TiC
3. Ti+Al → TiAl
4. $10/3\ Al+TiO_2+B_2O_3 \rightarrow TiB_2+ 5/3\ Al_2O_3$

The surfaces resulting from reactions 1 and 2 above had lower porosity than those produced by reactions 3 and 4.

Fused silica specimens coated with titanium carbide (Examples 1 and 2) were immersed in molten aluminum at 700° C and kept in the melting furnace for 7 days. For comparison uncoated fused silica specimens were also subjected to the same test. At the end of 7 days, samples were cut along their cross-sections and tested. In the ceramic specimens coated with titanium carbide, diffusion of aluminum into the ceramic body was not observed. In contrast to this, aluminum penetration to a depth of 0.5 mm occurred in the uncoated specimens.

The slurry of Example 5 was applied by dipping silica crucibles two or three times at 5 second intervals to obtain a coating thickness of 150-200 microns. After coating, samples were dried for 10 hours. The coated crucibles were then placed in a furnace which reached 1200° C in 2 hours and held at that temperature for 4 hours. The resulting combustion synthesis reaction (by thermal explosion mode in air) was as follows:

5. $Al_2O_3+2Ti+C+O_2 \rightarrow Al_2O_3+TiO_2+TiC$

Molten stainless steel was then poured into the coated silica crucibles. It was found that these crucibles could be reused for several heats of molten stainless steel. By way of comparison, an uncoated silica crucible could be used for only one heat due to extensive surface damage.

Numerous tests have been conducted on slurries of the invention for use in joining metallic surfaces. The following test procedures were used:

A - Samples in the form of rods (0.54 cm diameter, 5 cm length) were clamped in a Gleeble machine with the combustible slurry between the rod ends, using various joint geometries. (The Gleeble is a standard thermomechanical apparatus which applies both stress and temperature to a sample.) Current was then passed through each sample until the mixture reached ignition temperature and underwent combustion.

B - Bars of various sizes were butted together with a slurry in MAP between them. Another

combustible slurry was spread around the joint and ignited using an oxyacetylene torch. After combustion the slurry outside the joint was then chipped off.

C - Bars of various sizes were butted together, using a butt joint, with a slurry between the abutting ends and ignited by an oxyacetylene torch.

D - Mild steel bars of various thicknesses were joined using a silver brazing alloy foil in the joint and a combustible slurry around the outside of the joint.

The compositions, in weight percent, of the powdered constituents were as follows:

Example 6 - titanium dioxide 30%, boron oxide 26.25%, aluminum 33.75%, titanium 3.25%, boron 1.75%, nickel 4.1%, phosphorus 0.9%;

Example 7 - titanium 65%, boron 35%;

Example 8 - titanium 32.5%, boron 17.5%, nickel 41%, phosphorus 9%;

Example 9 - titanium dioxide 16.67%, boron oxide 14.58%, aluminum 18.75%, titanium 16.25%, boron 8.75%, nickel 20.5%, phosphorus 4.5%;

Example 10 - chromic oxide 68.5%, carbon 7.2%, aluminum 24.3%.

Slurries were prepared of all the above examples in MAP by mixing 1 gram of the powder with 0.3 cc of

MAP. Maximum reaction temperatures were determined in preliminary tests, and it was found that the highest reaction temperature was achieved by Example 6. This composition was therefore used in further tests.

Test data on the four procedures by which rods or bars were joined are tabulated below. While results were not uniformly successful with the slurries of the invention, comparison of joints prepared by procedure D with a conventional fusion welded joint using an oxyacetylene torch indicated that joint strength when using an optimum amount of slurry was generally comparable with joint strength obtained by conventional welding. In this connection the joint thickness was found to have a marked effect on joint strengths both for procedure D and conventional fusion welded joints, as shown in Table 5.

PROCEDURE A

Table 1

Slurry composition (in MAP)	Joint geometry	Result
	Stainless Steel Rods	
Ex. 8	Lap joint	Did not weld to surface of either rod.
Ex. 8	Mortise and tenon joint	Rods welded but broke apart when hit at joint.
Ex. 8+ 33%Al-67%Fe	Mortise and tenon joint	Rods welded but broke apart when hit at joint.
Ex. 9+ 10%Fe	Butt joint	Rods welded together. Combustion visible.
	Aluminum Rods	
Ex. 8+ 33%Al-67%Fe	Mortise and tenon joint	Rods welded but broke apart when hit at joint.
Ex. 8	Butt joint	Welded to surface of one rod.

PROCEDURE B

Table 2

Bar dimensions in cms.	Slurry inside joint	Slurry outside joint	Result
Stainless Steel Bars			
0.515x2x1.5	Ex. 9+ Cu (9:1)	Ex. 8	Bars welded but broke when bent by hand.
0.515x2x1.5	Ex. 9+ Cu (1:4)	Ex. 8	Bars welded but broke when bent by hand.
Aluminum Bars			
0.515x2x1.5	Ex. 9+ Cu (9:1)	Ex. 8	Bars welded but broke when bent by hand.
0.515x2x1.5	Ex. 9+ Cu (3:2)	Ex. 8	Bars welded but broke when bent by hand.
Mild Carbon Steel Bars			
0.336x3x15	Ex. 6+ Ag (1:1)	Ex. 6	Bars not welded
0.31x0.9.1.2	Ex. 6+ Ag (3:1)	Ex. 6	Bars welded together.

1	0.266x1.5x2	Ex. 6+ Ag (1:1)	Ex. 6	Bars not welded
	0.266x1.5x2	Ex. 6+ Ag (1:1)	Ex. 6	Bars welded together.
	0.266x1.5x2	14% Ex. 7+ 14% Ex. 10+ Ni-31.5%Al	Ex. 6	Bars welded together. X-ray examination of cut & polished section of weld indicated presence of Ni.
		Copper Bars		
	0.515x2x1.5	Ex. 6+ Cu-7.4%P (1:1)	Ex. 6	Bars not welded
	0.515x2x1.5	Ex. 6+ Cu-7.4%P (7:3)	Ex. 6	No combustion inside joint.
	0.515x2x1.5	Cu-7.4%P	Ex. 6	Bars welded together. Cu-7.4%P melted.
	0.515x2x1.5	Cu-7.4%P	Ex. 6	Bars welded together. More uniform melting of Cu-7.4%P.
	0.515x2x1.5	Cu-7.4%P +30%Al	Ex. 6	No combustion inside joint.

PROCEDURE C

Table 3

Bar dimensions in cms.	Slurry inside joint	Result
	Copper Bars	
0.515x2x1.5	Ex. 7	Combusted but did not weld.
0.515x2x1.5	Ex. 6+ Cu-7.4%P (4:6)	Bars not welded
0.515x2x1.5	Ex. 6+ Cu-7.4%P (7:3)	Bars not welded
	Mild Carbon Steel Bars	
0.266x1.5x2	Ex. 10	Did not combust.
0.266x1.5x2	90% Ex. 10 +10% Ex. 7	Did not combust.
0.266x1.5x2	Ex. 7	Fully combusted but not welded.

PROCEDURE D

Table 4

Mild Carbon Steel Bars

Bar dimensions (in cms)	Inside Joint	Outside Joint	Joint strength of welds: (1) 40 gms slurry (2) 20 gms slurry
0.266x2.98x15	Ag foil	Ex.6	(1) 68 MPa (2) 63 MPa
0.291x2.98x15	Ag foil	Ex.6	(1) 58 MPa (2) 38 MPa
0.3365x2.98x15	Ag foil	Ex.6	(1) 52 MPa (2) 32 MPa

Table 5

Joint thickness (in cms)	Joint strength of welds		
	40 gms slurry	20 gms slurry	Fusion weld oxyacetylene torch
0.266	68	63	80
0.291	58	38	68
0.3365	52	32	56

CLAIMS:

1. A slurry for joining metallic or ceramic surfaces or for coating metallic or ceramic and refractory surfaces, said slurry comprising a liquid suspending medium and at least two constituents suspended in particulate form in said medium and selected from the group consisting of titanium dioxide, boron oxide, aluminum oxide, aluminum, silicon, titanium, boron, nickel, phosphorus, chromic oxide, carbon, niobium, zirconium, tantalum, molybdenum, hafnium, and vanadium, said constituents being so selected and proportioned as to undergo exothermic reaction by combustion synthesis when ignited.

2. The slurry of claim 1, wherein said liquid suspending medium is monoaluminum phosphate or colloidal silica.

3. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 28% to 32% titanium dioxide, 25% to 27% boron oxide, 32% to 35% aluminum, 3% to 4% titanium, 1.5% to 2.0% boron, 3.8% to 4.5% nickel, and 0.7% to 1.1% phosphorus.

4. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 60% to 70% titanium, and 30% to 40% boron.

5. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 30% to 35% titanium, 15% to 20% boron, 38% to 44% nickel, and 8% to 10% phosphorus.

6. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 12% to 20% titanium dioxide, 10% to 16% boron oxide, 15% to 20% aluminum, 0% to 10% iron, 15% to 17.5% titanium, 8% to 9.5% boron, 19% to 22% nickel, and 4% to 5% phosphorus.

7. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 67% to 70% chromic oxide, 6.5% to 8% carbon, and 23% to 26% aluminum.

8. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 75% to 85% titanium, and 15% to 25% crystalline carbon.

9. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 75% to 85% titanium, and 15% to 25% amorphous carbon.

10. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 50% to 97.5% aluminum oxide; 2% to 25% titanium, and 0.5% to 25% amorphous carbon.

11. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 60% to 68% titanium, and 32% to 40% aluminum.

12. The slurry of claim 1, wherein said constituents comprise, in weight percent, from 30% to 36% titanium dioxide, 27% to 31% boron oxide, and 35% to 41% aluminum.

13. The slurry of claim 1, wherein said

constituents have an average particle size of less than 53 microns (-270 mesh screen).

14. The slurry of claim 1, including particulate diluents selected from the group consisting of aluminum, iron, copper, silver, borides, carbides, nitrides, and silicides of titanium, niobium, and chromium, and mixtures thereof.

15. The slurry of claim 2, wherein from about 8 to about 12 parts by weight of said constituents in particulate form are dispersed uniformly in about 2 to about 5 parts by volume of said liquid suspending medium.

16. A slurry for coating metallic or ceramic and refractory surfaces, comprising a liquid suspending medium and particulate constituents suspended in said medium capable of undergoing exothermic reaction by combustion synthesis when ignited, said constituents being selected from the group consisting of titanium and crystalline carbon; titanium and amorphorus carbon; titanium and aluminum; aluminum, titanium dioxide, and boron oxide; aluminum oxide, titanium, and amorphous carbon; and mixtures thereof.

17. The slurry of claim 16, wherein said liquid suspending medium is monoaluminum phosphate and/or colloidal silica.

18. The slurry of claim 16, wherein said constituents comprise, in weight percent, from 75% to 85% titanium, and 15% to 25% crystalline or

amorphous carbon.

19. The slurry of claim 16, wherein said constituents comprise, in weight percent, from 50% to 97.5% aluminum oxide, 2% to 25% titanium, and 0.5% to 25% amorphous carbon.

20. The slurry of claim 16, wherein said constituents comprise, in weight percent, from 60% to 68% titanium, and 32% to 40% aluminum.

21. The slurry of claim 16, wherein said constituents comprise, in weight percent, from 35% to 41% aluminum, 30% to 36% titanium dioxide, and 27% to 31% boron oxide.

22. The slurry of claim 16, wherein said constituents have an average particle size of less than 53 microns (-270 mesh screen).

23. The slurry of claim 18, wherein the average particle size of titanium is greater than that of crystalline carbon.

24. The slurry of claim 17, wherein about 1 part by weight of said constituents in particulate form is dispersed uniformly in about 1 to 2 parts by volume of said liquid suspending medium.

25. A slurry for joining metallic or ceramic surfaces, comprising a liquid suspending medium and particulate constituents suspended in said medium capable of undergoing exothermic reaction by combustion synthesis when ignited, said constituents being selected from the group

consisting of titanium dioxide, boron oxide, aluminum, titanium, boron, nickel and phosphorus; titanium and boron; titanium, boron, nickel and phosphorus; chromic oxide, carbon and aluminum; and mixtures thereof.

26. The slurry of claim 25, wherein said liquid suspending medium is monoaluminum phosphate or colloidal silica.

27. The slurry of claim 25, wherein said constituents comprise, in weight percent, from 28% to 32% titanium dioxide, 25% to 27% boron oxide, 32% to 35% aluminum, 3% to 4% titanium, 1.5% to 2.0% boron, 3.8% to 4.5% nickel, and 0.7% to 1.1% phosphorus.

28. The slurry of claim 25, wherein said constituents comprise, in weight percent, from 60% to 70% titanium, and 30% to 40% boron.

29. The slurry of claim 25, wherein said constituents comprise, in weight percent, from 30% to 35% titanium, 15% to 20% boron, 38% to 44% nickel, and 8% to 10% phosphorus.

30. The slurry of claim 25, wherein said constituents comprise, in weight percent, from 15% to 20% titanium dioxide, 13% to 16% boron oxide, 17% to 20% aluminum, 15% to 17.5% titanium, 8% to 9.5% boron, 19% to 22% nickel, and 4% to 5% phosphorus.

31. The slurry of claim 25, wherein said constituents comprise, in weight percent, from 67%

to 70% chromic oxide, 6.5% to 8% carbon, and 23% to 26% aluminum.

32. The slurry of claim 25, wherein said constituents have an average particle size of less than 53 microns (-270 mesh screen).

33. A method of coating metallic or ceramic and refractory surfaces whereby to provide chemically resistant coatings having decreased porosity, said method comprising the steps of providing a slurry having a liquid suspending medium and particulate constituents suspended in said medium capable of undergoing exothermic reaction by combustion synthesis when ignited, said constituents being selected from the group consisting of titanium and crystalline carbon; titanium and amorphous carbon; titanium and aluminum; aluminum, titanium dioxide, and boron oxide; aluminum oxide, titanium and amorphous carbon; and mixtures thereof; applying said slurry to a metallic, ceramic or refractory surface so as to form a layer of uniform thickness thereon; and igniting said layer to cause combustion synthesis thereof; thereby forming an adherent coating of titanium carbide; titanium aluminide; or a titanium boride and aluminum oxide composite.

34. The method of claim 33, wherein said step of igniting said layer comprises a wave propagation mode or a thermal explosion mode of reaction in air.

35. The method of claim 33, wherein said step of applying said slurry comprises painting, spraying or dipping to form a layer having a

thickness of about 0.2 to 0.3 mm.

36. The method of claim 33, wherein said liquid suspending medium is monoaluminum phosphate or colloidal silica.

37. A method of joining metallic or ceramic surfaces, which comprises the steps of providing a slurry having a liquid suspending medium and particulate constituents suspended in said medium capable of undergoing exothermic reaction by combustion synthesis when ignited, said constituents being selected from the group consisting of titanium dioxide, boron oxide, aluminum, titanium, boron, nickel and phosphorus; titanium and boron; titanium, boron, nickel and phosphorus; chromic oxide, carbon and aluminum; and mixtures thereof; applying said slurry to metallic or ceramic surfaces to be joined; placing said metallic or ceramic surfaces in abutting relation with said applied slurry therebetween; and igniting said slurry to cause combustion synthesis thereof at a temperature sufficient to fuse said metallic or ceramic surfaces together.

38. The method of claim 37, including the step of applying additional slurry around said metallic surfaces after placing said surfaces in abutting relation.

39. The method of claim 37, including the steps of placing a brazing alloy foil between said metallic surfaces, and applying additional slurry around said metallic surfaces after placing said surfaces in abutting relation.

40. The method of claim 37, wherein said liquid suspending medium is monoaluminum phosphate or colloidal silica.

INTERNATIONAL SEARCH REPORT

International Application No PCT/US 93/00661

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all)[6]

According to International Patent Classification (IPC) or to both National Classification and IPC

Int.Cl. 5 B23K35/34; C04B37/00; C04B37/02; C04B41/87
C23C24/08; C04B41/88

II. FIELDS SEARCHED

Minimum Documentation Searched[7]

Classification System	Classification Symbols
Int.Cl. 5	B23K ; C04B ; C23C

Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched[8]

III. DOCUMENTS CONSIDERED TO BE RELEVANT[9]

Category °	Citation of Document,[11] with indication, where appropriate, of the relevant passages[12]	Relevant to Claim No.[13]
X	CHEMICAL ABSTRACTS, vol. 104, no. 18 Columbus, Ohio, US; abstract no. 154386h, Y. MIYAMOTO ET AL. 'Bonding of metals and ceramics' see abstract & JP,A,60 251 177 (OSAKA UNIVERSITY ET AL.) ---	1,4,8,9, 13,16, 18,22, 23,25, 28,32
X	CHEMICAL ABSTRACTS, vol. 114, no. 8 Columbus, Ohio, US; abstract no. 67830m, E. UDAGAWA 'Formation of titanium diboride sintered layer on ceramic or metal substrates' see abstract & JP,A,02 155 728 (FUJITSU LTD.) --- -/--	1,4,13, 25,28,32

° Special categories of cited documents :[10]

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report
19 OCTOBER 1993	26.10.93
International Searching Authority	**Signature of Authorized Officer**
EUROPEAN PATENT OFFICE	HAUCK H.N.

Form PCT/ISA/210 (second sheet) (January 1985)

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category °	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 11, no. 394 (C-465)(2841) 23 December 1987 & JP,A,62 156 271 (AGENCY OF INDUSTRIAL SCIENCE & TECHNOLOGY) see abstract	1,4,25, 28
X	US,A,4 131 473 (R.H. KACHIK ET AL.) 26 December 1978	1
A	see claims 1-4	7,31
X	US,A,2 496 971 (S.B. WICZER) 7 February 1950	1
A	see claims 1,2	7,31

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.

US 9300661
SA 70029

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 19/10/93

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
US-A-4131473	26-12-78	US-A-	3963451	15-06-76
		BE-A-	810989	13-08-74
		CA-A-	1042321	14-11-78
		DE-A-	2406579	29-08-74
		FR-A,B	2217433	06-09-74
		GB-A-	1452697	13-10-76
		JP-C-	1160315	25-07-83
		JP-A-	50110938	01-09-75
		JP-B-	57056552	30-11-82
		JP-A-	57174460	27-10-82
		JP-B-	59007787	21-02-84
		US-A-	3947254	30-03-76
		US-A-	3946793	30-03-76
US-A-2496971		None		

EPO FORM P0479